

DOUGLAS FIR

THICKNESS X WIDTH
FACE COVER: 27x70 mm
WOOD SPECIE: Douglas Fir
BOARD: Brushed solid wood

PROFILE: Parallélo 30 SHADE: Gris 102

Ref. 424





CHARACTERISTICS

- Solid wood board.
- Kiln dried to 18% (+/-2%).
- Parallélo 30 profile, end-matched: facilitates the fitting and reduces the cutting wastage.
- Brushed surface: it gives an optimal and texture surface; it brings out the natural grain and increases penetration and efficiency of the coating.
- Class 3.1 preservation, CTBB+ certified, sprayed on the 4 sides.
- New generation preservation: fungicide, anti-bluestain, insecticide, anti-termite.
- Finish:
 - > Water-based penetrating finish made with acrylic resin and natural mineral pigment (chemical free).
 - Industrial quality finish applied under strictly controlled factory conditions, ensuring consistent and unifrom application.
 - > Application of a finish on the reverse side ensuring a good balance of the board.
- The durability of the wood is guaranteed for 10 years with preservation.
- The Sivalbp-New Age finish allows to delay the natural ageing process for minimum 3 years, according to exposure and building's architecture. Douglas fir, lasting up to 50 years.

SHADE: GRIS 102



WOOD SPECIE: DOUGLAS FIR

Douglas Fir: French timber, lasting up to 50 years, **PEFC** certified (**PEFC/10-31-1593**).

Singularities and knots: fast-growing essence; medium veining; medium to large knots; marked singularities.









| WOOD SPECIE | | THERMAL PROCESS | DURABILITY | TE | ECHNICAL PROPERTIE | ES |
|--|------|---|-------------------------------------|-----------------------------------|--|--|
| Douglas Fir Geographical area: wood specie sourced in France Quality: A/B choice NF EN 14519 A fast-growing specie, characterised by a marked-grain, a pink colour and the presence of tight sound knots. PEFC certified | | | Use class: 3.1 | Behavioural fire restrictions | Thermal characteristics according to NF EN 12 524 | Water vapour permeability according to NF EN 12 524 |
| | | Kiln dried to 18% (+/- 2%) guaranteeing the stability of boards and a better lasting of the finish | preservation certified CTB B+ | Reaction to fire: NPD* | Thermal resistance R | Water vapour resistance: 72 µ |
| | FDES | | Douglas Fir, lasting up to 50 years | Combustible mass in MJ/m²: 239 | in m ² . K/W: 0,13 | Average density: 525 kg/m³ to 12% wood moisture content |

| (module D excluded)* | | | | | | , | - ' | | | content |
|---|----------------|--|---------|---------------------------------|--|----------|--|--------------|--|---------------------------|
| Consult our Environmental and | d Health Decla | ration Sh | eets on | the INIES database | | | | | | |
| | | | | MEC | HANICA | AL PROPE | RTIES | | | |
| Breaking stress in compression: 55 Nm/mm² | | stress in tension: 3 N/mm² Breaking stress in sho 9,5 | | shear: | hear: Breaking stress in bending: 85 N/Nm² | | Modulus of elasticity in bending: 12 100 n/mm² | | | |
| Preparation Finish | SH | lade | | CKNESS X WIDTH E COVER IN MM | | ARD | LENGTHS (M)* (saccording to availability | r) | FITTING | PACKAGING |
| Brushed solid wood 1 coat of saturator by sprayi the facing 1 coat of white stain for coa balancing | ing on Gri | s 102 | | 27x70 mm | Brushe wo | | 4.00 m | of t cm c | rail in the center the slat for a 40 distance between centres suble up the nails at the ends distallation advice below | Packs x boards/pack: 72x6 |

* NPD : No Performance Determined.

INSTALLATION ADVICES



To ensure the products are correctly installed, the rules laid out in the French code of practice DTU 41.2 for external cladding, and our Technical Guide, should be observed.

- Store the boards in a dry place, sheltered from the elements and ventilated.
- Can be fitted horizontally or vertically (mandatory double battening for vertical installation).
- Cladding must be fixed on batten with a minimum of 27 mm thickness (32 mm for UK).
- The distance of the secondary framework must be attached at a minimum of 40 cm and a maximum of 65 cm apart. Single fixing on visible cladding for 40 cm distance between centers. Double fixing on visible cladding for a distance between centres between 40 cm and 65 cm maximum.
- A waterproof membrane satisfying the standard must be installed (except for walls which are already watertight, solid concrete walls).
- Mandatory air gap behind Sivalbp cladding to ensure a good ventilation. The air outlets must be at the base and the top of the cladding elevation.
- Ensure a minimum of 20 cm above ground clearance.
- Assembly by interlocking (end-matched on the 4 sides)
- Fastening with stainless steel screws or stainless steel tips, twisted or ringed.
- The head of the nails or screws must not penetrate further than mm into the boards.
- All the cuts must be touched up with Sivalbp-New Age paint. We also recommend that the ends of the boards should also be treated

GENERAL REMARK

Wood is a natural and heterogeneous material, subject to varying degrees of dimensional variations, depending on humidity and climatic conditions. These factors can cause, among others, cracking, resin exudation, shrinkage and curling. The wood may have singularities such as knots, cracking, splits, resin exudation,

ACCESSORIES AND FINISH CUTS TOUCH UP

- Accessories available in 1 shade: gris 102.
- Available finish cuts touch up in tins of 1L or 5L: all cuts must be touched up (see French DTU 59.1)

| Profile | | | | |
|------------------------------------|---------------------------|------------|--|--|
| Product | Complex corner trim | Board | | |
| Surface finish | Sanded finger- jointed | Solid wood | | |
| Thickness x width face cover in mm | 67x55 | 25×275 | | |

MAINTENANCE

- To maintain the bright of colors, clean annually by lightly brushing the surface (avoid high pressure cleaners).
- This gray finish will evolve naturally and very gradually over time.
- If necessary and according to the exposure and the architecture of the building, renovation of the color is facilitated without stripping or sanding.
- As soon as necessary, apply Sivalbp New Age saturator directly a spray or paintbrush in 1 or 2 coats to re-saturate the wood
- A sustained finish will help to preserve the cladding.
- We advise you to contact a professional who will apply the appropriate renovation procedure.



Find all of our **DOCUMENTATION** on our website: sivalbp.fr



TECHNICAL GUIDE



Download our **MAINTENANCE BOOKLET** for our maintenance

