SIVALBP NEW AGE

EXTERNAL CLADDING TIMELESS GREY SATURATORS

NORDIC SPRUCE

THICKNESS X WIDTH
FACE COVER: 20x130 mm
WOOD SPECIE: Nordic Spruce
BOARD: Brushed solid wood

PROFILE: Linéa Évo
SHADE: Irisé 108
Ref. A48

sivalbp
bois, technologie & design

SIVALBP

- A trendy pearl grey which preserves the natural look of wood.
- A protection against UV, chemical free and waterproof.
- A non film forming finish that penetrates into the wood and does not flake over time.

PROFILE: LINÉA ÉVO 20x130

END-MATCHED

- **Optimised width face cover.**
- **Rounded edges** for a better lasting of the finish.
- **Secret nail** for a maximum wood moisture content of 18%.
- **Conical tongue:** better fitting and quick to install.
- **End-matched:** simplifies installation and reduces the cutting wastage.

CHARACTERISTICS

- Kiln dried to 18% (+/- 2%).
- **Linéa Evo profile, end-matched:** facilitates the fitting and reduces the cutting wastage.
- **Brushed surface:** it gives an optimal and texture surface; it brings out the natural grain and increases penetration and efficiency of the coating.
- **Class 3.1 preservation, CTBB+ certified, sprayed on the 4 sides**.
- New generation **preservation**: **fungicide, anti-bluestain, insecticide, anti-termite**.
- Finish:
  - > **Water-based penetrating finish made with acrylic resin and natural mineral pigment** (chemical free).
  - > Industrial quality finish applied under strictly controlled factory conditions, ensuring consistent and unifrom application.
  - > Application of a finish on the reverse side ensuring a good balance of the board.
- The durability of the wood is guaranteed for 10 years with preservation.

SPECIFIC RECOMMENDATIONS

This product is not recommended for low protection architectures (without eaves).

SHADE: IRISÉ 108

WOOD SPECIE: NORDIC SPRUCE

Nordic Spruce: Scandinavian timber, PEFC certified (PEFC/10-31-1593), lasting up between 10 to 30 years (3.1 class). Singularities and knots: slow-growing essence; small to medium knots; clear wood.

PEFC 10-31-1593 Promoting Sustainable Forest Management www.pefc-france.org

REACTION TO FIRE EUROCLASS D

MADE IN FRANCE

FDES inies

CTBB+

CE NF EN 14915

All our boards are compliant with CE marking

NORDIC SPRUCE

Thickness x width face cover: 20x130 mm
Brushed solid wood - Linéa Évo - Irisé 108 - Ref. A48

WOOD SPECIE		THERMAL PROCESS	DURABILITY	TECHNICAL PROPERTIES		
Nordic Spruce		**Kiln dried to 18%** (+/- 2%) guaranteeing the stability of boards and a better lasting of the finish	**Use class: 3.1** with the Sivalbp preservation certified CTB B+	**Behavioural fire restrictions**	**Thermal characteristics according to NF EN 12 524**	**Water vapour permeability according to NF EN 12 524**
Geographical area: Scandinavia Quality: A/B choice NF EN 14519				EUROCLASSE D-s2, d0 for reaction to fire (according to french PV Feu N° EFR-23-005372-REV1)	Thermal resistance R in m^2. K/W: 0,12	Water vapour resistance: 66 µ
PEFC certified			Nordic Spruce, lasting up between 10 to 30 years	Combustible mass in MJ/m^2: 164		Average density: 475 kg/m^3 to 12% wood moisture content
Carbon footprint: 6.29 kg CO_2 eq./m^2 (module D excluded)*	FDES INIES					

* Consult our Environmental and Health Declaration Sheets on the INIES database

MECHANICAL PROPERTIES					
Breaking stress in compression: 45 N/mm^2	Breaking stress in tension: 85 N/mm^2	Breaking stress in shear: 6	Breaking stress in bending: 71 N/mm^2	Modulus of elasticity in bending: 12 100 N/mm^2	Compliant for French implementation in Q4 area (impact resistance)

PREPARATION FINISH	SHADE	THICKNESS X WIDTH FACE COVER IN MM	BOARD	LENGTHS (M)* (saccording to availability)	FITTING	PACKAGING
Brushed solid wood 1 coat of saturator by spraying on the facing 1 coat of white stain for counter-balancing	**Irisé 108**	20x130 mm	Brushed solid wood	3.90 - 4.20 - 4.50 - 4.80 - 5.10 m	2 nails (find installation advice below)	Packs x boards/pack: 48x4

*For solid wood boards with end-matched, the effective length is equal to the standard supply length invoiced minus 30 millimeters.

INSTALLATION ADVICES

To ensure the products are correctly installed, the rules laid out in the French code of practice DTU 41.2 for external cladding, and our Technical Guide, should be observed.

- xStore the boards in a dry place, sheltered from the elements and ventilated.
- Can be fitted **horizontally or vertically** (mandatory double battening for vertical installation).
- Cladding must be fixed on batten with a minimum of 27 mm thickness (32 mm for UK).
- They must be attached at a minimum of 40 cm and a maximum of 65 cm apart (60 cm for UK).
- A waterproof membrane satisfying the standard must be installed (except for walls which are already watertight, solid concrete walls).
- **Mandatory air gap** behind Sivalbp cladding to ensure a good ventilation. The air outlets must be at the base and the top of the cladding elevation.
- Ensure a minimum of 20 cm above ground clearance.
- Assembly by interlocking (end-matched on the 4 sides).
- Fastening with **stainless steel screws or stainless steel tips**, twisted or ringed – 2 nails, 1 visible nail in the upper part of the board, locked in the upper third of the board + 1 visible nail in the lower part of the board, locked at least 15 mm from the groove.
- The head of the nails or screws must not penetrate further than 1 mm into the boards.
- **All the cuts must be touched up with Sivalbp-New Age paint.** We also recommend that the ends of the boards should also be treated.

ACCESSORIES AND FINISH CUTS TOUCH UP

- Accessories available in 1 shade: irisé 108.
- Available finish cuts touch up in tins of 1L or 5L: all cuts must be touched up (see French DTU 59.1)

Profile	
Product	Corner trim
Surface finish	Sanded finger-jointed
Thickness x width face cover in mm	13x58x58

MAINTENANCE

- To maintain the bright of colors, clean annually by lightly brushing the surface (avoid high pressure cleaners).
- To extend the aesthetic durability of the cladding over time, plan for maintenance within 4 to 6 years after installation following the exposure of the facade and the architecture of the building.
- As soon as necessary, apply Sivalbp **New Age** saturator directly a spray or paintbrush in 1or 2 coats to re-saturate the wood fibers.
- A sustained finish will help to preserve the cladding.

GENERAL REMARK

Wood is a natural and heterogeneous material, subject to varying degrees of dimensional variations, depending on humidity and climatic conditions. These factors can cause, among others, cracking, resin exudation, shrinkage and curling.The wood may have singularities such as knots, cracking, splits, resin exudation, etc.

Find all of our **DOCUMENTATION** on our website: **sivalbp.fr**

Get our installation advice in the SIVALBP **TECHNICAL GUIDE**

Download our **MAINTENANCE BOOKLET** for our maintenance recommendations

sivalbp® bois, technologie & design