# NORDIC PINE (ECOTHERMO)

THICKNESS X WIDTH FACE COVER: 27x125 mm WOOD SPECIE: NORDIC PINE (EcoThermo) BOARD: Brushed solid wood PROFILE: Soléa II SHADE: Café 111 Ref. 566



## PROFILE: SOLÉA II 27x125



- Rounded edges for a better lasting of the finish.
- Nailing line: easy installation.
- Secret nail for a maximum wood moisture content of 18%.
- Conical tongue: better fitting and quick to install.
- **End-matched:** simplifies installation and reduces the cutting wastage.

## **CHARACTERISTICS**

- EcoThermo solid wood board.
- Soléa II profile, one secret nail on the nailing line, endmatched: facilitates the fitting and reduces the cutting wastage.
- **Brushed surface:** it gives an optimal and texture surface; it brings out the natural grain and increases penetration and efficiency of the coating.
- Thermostabilised boards will clear up in the first weeks under the effect of UV and according to exposure and building's architecture.
- Class 3.1 preservation, CTBB+ certified, sprayed on the 4 sides.
- New generation preservation: fungicide, anti-bluestain, insecticide, anti-termite.
- Finish:
  - > Water-based penetrating finish made with acrylic resin and natural mineral pigment (chemical free).
  - Industrial quality finish applied under strictly controlled factory conditions, ensuring consistent and unifrom application.
  - > Application of a finish on the reverse side ensuring a good balance of the board.
  - The durability of the wood is guaranteed for 10 years with preservation.
- The Sivalbp-**Vintage** finish allows to delay the natural ageing process for minimum 3 years, according to exposure and building's architecture. Nordic Pine, lasting up to 50 years.

## 

 EcoThermo cladding, environmentally friendly.

- Vintage colours revisited.
- Preserves the natural look of wood.
- A protection against UV, chemical free and waterproof.
- A non film forming finish that penetrates into the wood and does not flake over time.
  Easy maintenance, allows naturally evolving wood.

## SHADE: CAFÉ 111



### WOOD SPECIE: NORDIC PINE (ECOTHERMO)

**Nordic Pine:** Scandinavian timber, lasting up to 50 years, 3 class thanks to thermostabilisation, **PEFC certified (PEFC/10-31-1593)**. Exceptional durability and stability.





Friendly environmentally process and chemical free Exceptional durability and stability Better resistance to the weather





### NORDIC PINE (ECOTHERMO) Thickness x width face cover: 27x125 mm Brushed solid wood - Soléa II - Café 111 - Ref. 566

| WOOD SPECIE   |      | THERMAL PROCESS DURABILITY TECHNICAL PROPERTIES  |  |   | S                             |  |
|---|------|--|--|---|-------------------------------|--|
| Nordic Pine<br>Geographical area: Scandinavia<br>Quality: A/B choice NF EN 14519<br>Thanks to the thermostabilisation, Nordic<br>Pine becomes an excellent material for an<br>external use.<br>PEFC certified |      | Thermostabilisation<br>Ecological process,<br>environmentally friendly and<br>chemical free. It consists in  | Use class: 3.1<br>with the Sivalbp     | Behavioural fire characteristics perme<br>restrictions according to NF EN according             |                               | Water vapour<br>permeability<br>according to NF EN<br>12 524                 |
|   |      | This process gives the boards<br>exceptional durability and  | preservation certified<br>CTB B+       | EUROCLASSE D-s3, d0<br>for reaction to fire<br>(according to 14915+A1 : 2017 EN NF<br>standard) | - Thermal resistance R        | Water vapour<br>resistance: 72 µ   |
| Carbon footprint:<br>6.29 kg CO <sub>2</sub> eq./m <sup>2</sup><br>(module D excluded)*   | FDES | stability and greatly reduces the<br>shrinkage phenomenon. The<br>wood acquires an even, brown<br>colour all the way through and<br>neutralizes resin exudation. | Nordic Pine, lasting<br>up to 50 years | Combustible mass<br>in MJ/m²: 136   | in m <sup>2</sup> . K/W: 0,13 | Average density:<br>520 kg/m <sup>3</sup><br>to 12% wood moisture<br>content |

\* Consult our Environmental and Health Declaration Sheets on the INIES database

#### MECHANICAL PROPERTIES

| Breaking stress in<br>compression:<br>NC* №m/mm <sup>2</sup>   | Breaking stress in tension:<br>NC* Nm/mm <sup>2</sup> |          | Breaking stress in shear:<br>NC             |                 | Breaking stress in bending:<br>NC N/nm <sup>2</sup> |  | Modulus of elasticity in<br>bending: NC N/mm <sup>2</sup>                  |                           |
|--|---|----------|---|-----------------|---|--|--|---------------------------|
| PREPARATION<br>FINISH  |   | SHADE    | THICKNESS<br>X WIDTH<br>FACE COVER<br>IN MM | BOAR            | RD  | LENGTHS (M)*<br>(according to availability)  | FITTING  | PACKAGING                 |
| Brushed solid wo<br>1 coat of wood preservative 3.<br>the four sides: 100 g<br>1 coat penetrating finsih on the<br>m <sup>2</sup><br>1 coat of white paint on the u<br>50 g/m <sup>2</sup> | .1 use class on<br>g/m <sup>2</sup><br>e side: 120 g/ | Café 111 | 27x125 mm                                   | Brushed<br>wood |   | 3.60 - 3.90 - 4.20 -<br>4.50 - 4.80 - 5,10 m | 1 secret nail on the<br>nailing line<br>(find insullation advice<br>below) | Packs x boards/pack: 48x4 |

\*For solid wood boards with end-matched, the effective length is equal to the standard supply length invoiced minus 30 millimeters. NPD: not performance declared. NC: non communicated.

## **INSTALLATION ADVICES**



#### To ensure the products are correctly installed, the rules laid out in the French code of practice DTU 41.2 for external cladding, and our Technical Guide, should be observed.

- Store the boards in a dry place, sheltered from the elements and ventilated.
- Can be fitted **horizontally or vertically** (mandatory double battening for vertical installation).
- Cladding must be fixed on batten with a minimum of 27 mm thickness (32 mm for UK).
- They must be attached at a minimum of 40 cm and a maximum of 65 cm apart (60 cm for UK).
- A waterproof membrane satisfying the standard must be installed (except for walls which are already watertight, solid concrete walls).
- **Mandatory air gap** behind Sivalbp cladding to ensure a good ventilation. The air outlets must be at the base and the top of the cladding elevation.
- Ensure a minimum of 20 cm above ground clearance.
- Assembly by interlocking (end-matched on the 4 sides).
- Fastening with **stainless steel screws or stainless steel tips**, twisted or ringed 1 secret nail fixed on the nailing line.
- The head of the nails or screws must not penetrate further than 1 mm into the boards.
- All the cuts must be touched up with Sivalbp-Vintage paint. We also recommend that the ends of the boards should also be treated.

## **GENERAL REMARK**

White marks may appear on the boards upon installation. This phenomenon, caused by an excess of nacre, is well known and does not affect the durability of the façade. These marks are purely aesthetic and naturally fade after a few months of UV exposure. However, if needed, they can be easily removed with a simple wipe of a cloth.

## ACCESSORIES AND FINISH CUTS TOUCH UP

- Accessories available in 1 shade: café 111
- Available finish cuts touch up in tins of 1L and 5L : all cuts must be touched up (see French DTU 59.1)

| Profile                               |                           |               |  |
|---------------------------------------|---------------------------|---------------|--|
| Product                               | Complex corner<br>trim    | Board         |  |
| Surface finish                        | Sanded finger-<br>jointed | Sanded glulam |  |
| Thickness x width<br>face cover in mm | 67x55                     | 25x270        |  |

## MAINTENANCE

- To maintain the shine of the colors, clean annually by lightly brushing the surface (avoid high pressure cleaners).
- The Sivalbp-Vintage finish does not flake. Color renovation made easier without stripping or sanding, if necessary and depending on the building's exposure and architecture.
- As soon as necessary, apply the Sivalbp-Vintage saturator directly with a spray gun or brush in 1 or 2 coats to re-saturate the wood fibers.
- A sustained finish will help to preserve the cladding.
- We advise you to contact a professional who will apply the appropriate renovation procedure.









1, RUE DU PETIT PESSEY - ZA LA BALMETTE - 74230 THÔNES - TEL. +33 (0)4 50 32 07 18 - SIVALBP.FR

SIVALBP VINTAG