

# RED DOUGLAS FIR

THICKNESS X WIDTH FACE COVER: 27x125 mm

WOOD SPECIE: Red Douglas Fir

BOARD: Planed solid wood

PROFILE: Affinéa

Ref. A46





- Conical tongue: better fitting and quick to install.
- End-matched: simplifies installation and reduces the cutting wastage.

#### **CHARACTERISTICS**

- Solid wood board.
- Kiln dried to 18% (+/-2%).
- Affinéa profile, one secret nail on the nailing line, endmatched: facilitates the fitting and reduces the cutting wastage.
- Planed wood board for a smooth appearance and remove roughness.
- The Sivalbp-Authentic range offers a range of unfinished products: the natural wood aesthetics.



#### **WOOD SPECIE: RED DOUGLAS FIR**

**Red Douglas Fir:** French timber, lasting up to 50 years, **PEFC certified**. Species characterised by a marked grain and the presence of tight sound knots.











## RED DOUGLAS FIR

Thickness x width face cover: 27x125 mm Planed solid wood - Affinéa - Ref. A46

WOOD SPECIE	THERMAL PROCESS	DURABILITY	TECHNICAL PROPERTIES		
Red Douglas Fir  Geographical area: France Quality: A/B choice NF EN 14519 A fastgrowing specie, characterised by	Kiln dried to 18% (+/- 2%) guaranteeing the stability of boards	Use class: 3.2 (without sapwood) according to FD P20-651	Behavioural fire characteristic according to NF 12 524		Water vapour permeability according to NF EN 12 524
A fast-growing specie, characterised by a marked-grain, a pink colour and the presence of tight sound knots.  PEFC certified			(according to 14915 standard) EUROCLASSE D-s2, d0 for reaction to fire	Thermal resistance R	Water vapour resistance: 72 µ
Carbon footprint: 1.29 kg CO <sub>2</sub> eq./m² (module D excluded)*		Red Douglas Fir, lasting up to 50 years	Combustible mass in MJ/m²: 186	in m <sup>2</sup> . K/W: 0,13	Average density: 525 kg/m³ to 12% wood moisture

MECHANICAL PROPERTIES								
Breaking stress in compression: 55 Nm/mm <sup>2</sup>	Breaking stress 93 N/m		Breaking stress in shear: 9,5		Breaking stress in bending: 85 N/Nm <sup>2</sup>	Modulus of elasticity bending: 12 100 n/r		
PREPARATION FINISH	SHADE		SS X WIDTH VER IN MM	BOARD	LENGTHS (M)* (according to availability)	FITTING	PACKAGING	
Planed solid wood	without finish	27x1	25 mm	Planed solid wood	3.00 - 3.50 - 4.00 - 4.50 - 5.00 m	FCBA Report: 1 secret nail on the nailing line (find installation advice below)	Packs x boards/pack: 48x4	

<sup>\*</sup>For solid wood boards with end-matched, the effective length is equal to the standard supply length invoiced minus 30 millimeters

#### **INSTALLATION ADVICES**



To ensure the products are correctly installed, the rules laid out in the French code of practice DTU 41.2 for external cladding, and our Technical Guide, should be observed.

- Store the boards in a dry place, sheltered from the elements and ventilated.
- Can be fitted horizontally or vertically (mandatory double battening for vertical installation).
- Cladding must be fixed on batten with a minimum of 27 mm thickness (32 mm for UK).
- They must be attached at a minimum of 40 cm and a maximum of 65 cm apart (60 cm for UK).
- A waterproof membrane satisfying the standard must be installed (except for walls which are already watertight, solid concrete walls).
- Mandatory air gap behind Sivalbp cladding to ensure a good ventilation. The air outlets must be at the base and the top of the cladding elevation.
- Ensure a minimum of 20 cm above ground clearance.
- Assembly by interlocking (end-matched on the 4 sides).
- Fastening with stainless steel screws or stainless steel tips, twisted or ringed - 1 secret nail fixed on the nailing line.
- The head of the nails or screws must not penetrate further than 1 mm into the boards.

#### **ACCESSORIES AND FINISH CUTS** TOUCH UP

• Accessories finger-jointed or glulam, sanded, Red Douglas fir.

Profile			
Product	Complex corner trim	Board	
Surface finish	Sanded finger- jointed	Solid wood	
Thickness x width face cover in mm	67x55	27x275	

#### MAINTENANCE

- Wood is a natural and not homogeneous material which can contain some particularities. Boards contain knots of various, for the greater part healthy dimaters and members.
- Living material, maintenance free, wood without finish can in the time present molds of surface, without compromising the durability of wood.
- Regarding the sustainability of aspect, it is underlined that woden species not dressed in finish will turn natural grey over

### **GENERAL REMARK**

Wood is a natural and heterogeneous material, subject to varying degrees of dimensional variations, depending on humidity and climatic conditions. These factors can cause, among others, cracking, resin exudation, shrinkage and curling.



our **DOCUMENTATION** on our website: sivalbp.fr



TECHNICAL GUIDE



Download our MAINTENANCE BOOKLET for our maintenance

